

# **ARDEX A36 Abascreed**

## **Premixed Sand Cement Screed**

Factory proportioned premixed sand/cement screed

Especially designed to achieve falls for water run-off

For internal and external use

Trafficable after 24 hours

Ready to receive tiles after 7 days

20 Powers Road Seven Hills NSW 2147 1300 788 780 technicalservices@ardexaustralia.com www.ardexaustralia.com

info@ardexnz.com www.ardex.co.nz

# **ARDEX A36 Abascreed**

## **Premixed Sand Cement Screed**

## **DESCRIPTION**

ARDEX A 36 Abascreed is a factory proportioned premixed sand/cement screed for internal and external use. It is especially designed to achieve falls for water run-off and to economically level uneven floors prior to tiling or waterproofing.

## TO SUBSTRATES

Concrete floors, fibre cement sheets, timber floors (internal)

## SUBSTRATE PREPARATION

Surfaces must be free from dust, oil, grease and all loose contaminating materials. Alternatively, use a separating layer (heavy-duty plastic sheet) to isolate the background from ARDEX A36. Ensure surfaces are dry with no residue or permanent damp.

### Concrete

This includes precast, in-situ and wood floated concrete. As concrete exhibits drying shrinkage, allow to cure for at least 4 weeks prior to tiling. Any surface laitance, concrete sealers, curing compounds, and other materials should be removed from the surface prior to tiling. Steel trowel finished concrete should be roughened mechanically to remove laitance and provide a good key. The concrete should have adequate surface profile (e.g. broom finish) to provide a mechanical key. Smooth surfaces and/or dense concrete greater than 35MPa must be mechanically roughened.

## **Fibre-Cement Sheets**

Fix sheets according to manufacturer's instructions making sure the surface is completely clean. Tape sheet joints with PVC duct tape or masking tape.

## **Timber Floors**

Timber floors must be structurally sound and free from abnormal deflection. The maximum load deflection must not exceed 1/360 of the span. Use a separating layer (heavy-duty plastic sheet) to isolate the background from ARDEX A 36.

## MIXING

ARDEX A 36 powder is added to clean water in a clean container and mixed thoroughly to give a moist semi-dry mix for optimal application. A 20kg bag of ARDEX A 36 requires approximately 2 litres of water. To achieve a stronger, more resilient screed and for all timber substrates, replace water with 3:1 water to ARDEX Abacrete dilution.

- 1. Pour clean water into a container and add ARDEX A 36, mix thoroughly to achieve a firm paste consistency.
- 2. Alternatively, create a mound of ARDEX A36, form a cavity in the centre and fill with required amount of water. Fold the powder over the water and combine until a firm, consistent mix is achieved.

  Do not apply at temperatures below 10°C.

## **APPLICATION**

A minimum thickness of 10mm is recommended when using diluted ARDEX Abacrete instead of water; 15mm when mixed with water. For a thickness greater than 40mm, reinforcing mesh is required.

1. Using a roller, paint brush or a flat trowel, coat the prepared area with a slurry of 2:1 neat cement: ARDEX Abacrete to improve adhesion of ARDEX A 36

- 11. Osing a roles, paint broad of a rata tower, coat the prepared area with a slurry of 2:1 neat cement: ARDEX Abacrete to improve adhesion of ARDEX A36 to the substrate. Slurry coat not required if isolating layer (plastic sheet) is used.
- 2. If necessary, cut plastic sheet to size allowing for 100mm overlap at joints and upturn at walls above screed height (trim after ARDEX A 36 sets). Tape overlapping sheet joints.
- 3. Apply the ARDEX A 36 mix whilst the slurry coat is still wet or screed directly over the plastic sheet.
  4. Use a straight edge, trowel or timber batten to level the material. Achieve falls in shower recesses to a minimum 1:60, internal wet areas (e.g, bathrooms) to a minimum of 1:80 and external areas to a minimum of 1:100. When reinforcing the screed with

galvanised mesh, apply first layer of ARDEX A 36 lay in the mesh and apply the second layer of A 36. Do not lay the mesh directly onto the substrate. ARDEX A 36 should be left with a wood float finish to create a key for tiling and waterproofing.

### DRYING TIME

ARDEX A 36 is trafficable after 24 hours at 23°C and 50% relative humidity with an initial set time of 3-5 hours. Tiling and waterproofing to take place after 7 days (23°C and 50% R.H.) Drying times will vary depending on humidity, surface temperature and porosity of substrates.

## **COVERAGE**

20kg of ARDEX A 36 is sufficient for approximately  $1\text{m}^2$ , at 10mm thickness. To achieve adequate falls to the waste, a  $1\text{m}^2$  shower base will require approximately 40kg of ARDEX A 36 (depending on minimum bed thickness).

## CLEAN UP

All tools should be cleaned with water immediately after use.

## **SHELF LIFE**

ARDEX A36 has a shelf life of 12 months when stored in the original unopened packaging, in a dry place at  $23^{\circ}\text{C}$  and 50% relative humidity

## Pay attention to the following:

Protect from wind and direct sunlight whilst ARDEX A36 is setting (3 - 5hours @ 23°C and 50% relative humidity).

Do not add sand as this will lower performance. Reinforce ARDEX A 36 with galvanised mesh in the following cases:

- screeds over 40mm
- when used in conjunction with a separating layer eg, heavy-duty plastic sheet
- for all framed construction (e.g, F/C sheets over joists).

ARDEX A 36 must be mixed with ARDEX Abacrete when used over timber substrates.

A minimum thickness of 40mm is required when ARDEX A 36 is unbonded i.e, over a separating layer such as heavy-duty plastic sheet; 15mm where screed is bonded directly; 10mm when mixed with ARDEX Abacrete.

Do not use 'chicken wire' as reinforcement. 25x25mm (min 0.8mm thick) galvanised mesh is recommended.

Keep water content in mixture to a minimum to avoid shrinkage.

Not intended for smoothing floors prior to installation of resilient floor coverings.

Keep damp with water for at least 7 days to reduce shrinkage stresses whilst curing.

## **TECHNICAL DATA**

Colour: Coarse Green Powder Mixing Ratio: 2.0L water per 20kg

Powder Bulk Density: 0f powder Powder Bulk Density: 1.65kg/L Mortar Density: 2.2kg/L

Mechanical Properties	With water @16%	With water: Abacrete (3:1) @ 16%
Compressive Strength	20.2MPa	22.6MPa
Flexural Strength	4.0	5.5

### SAFETY DATA

This product may cause irritation and an allergic reaction to the skin. It may cause serious eye injury and irritation to the respiratory system. In case of contact with the eyes rinse with running water until advised to stop by the Poisons Information Centre or a doctor, or for at least 15 minutes. Wear protective gloves, clothing, eye and face protection. Avoid inhaling dust/fumes/gas/mist/vapours/spray. Ensure adequate ventilation during mixing and application. Store locked up. Check with your local Council regarding the disposal of contents, dispose of packaging thoughtfully and recycle where possible. Keep out of the reach of children. Call the Poisons Information Centre on 131 126 (AUS) and 0800 764 766 (NZ) or call a doctor if you feel unwell. Additional information is in the Safety Data Sheet (SDS) at www.ardexaustralia.com.

## **GUARANTEE**

ARDEX Australia Ptv Ltd ("we" or "us") guarantees this product ("our goods") is free from manufacturing defects and will perform to any applicable specification published by us for 10 years from the date of purchase. Our liability under this guarantee is limited at our option to replacement of the product, repair of any damage to the immediate surface or area of application of the product, or compensation, in each case if we are satisfied loss or damage was due to a breach of this guarantee. This guarantee does not apply if damage or loss is due to failure to follow published instructions or any act or circumstance beyond our control, including shade variations and efflorescence. If you wish to make a claim under this guarantee you must notify us (ARDEX Australia Pty Ltd, 20 Powers Road Seven Hills NSW 2147; Toll Free: 1800 224 070; Email: technicalservices@ ardexaustralia.com) and provide evidence of your purchase of the product within 30 days of any alleged loss or damage occurring. We reserve the right to ask you for satisfactory evidence of any alleged loss or damage. Any claim under this guarantee is at your cost. This guarantee is in addition to any rights or remedies you may have as a "consumer" under the Australian Consumer Law and to that extent you need to be aware that: "Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and for compensation for any other reasonably foreseeable loss of damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure".

## DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable Australian Standards. Our instructions and recommendations are only for the uses they are intended. Users are advised to confirm that this product is suitable for their application and conforms with the specifications of the system. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may affect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

© ARDEX Australia Ltd 2019.

All aforementioned products are the trademarks of ARDEX Australia Ltd, its licensor's and affiliates.

This datasheet was issued in October 2019 and is valid for 3 years, in some instances a newer version may be published. Always refer to www.ardexaustralia.com for the latest technical data from ARDEX Australia Pty Ltd.