



---

# ARDEX WPM 150

## 3mm Plain Bitumen Membrane

---

Compliant to AS4654.1

Excellent elongation

Good elastic memory

Cold flexibility to  $-5^{\circ}\text{C}$

Combined Reinforced APP Bitumen Membrane

---

**ARDEX Australia Pty Ltd**  
2 Buda Way  
Kemps Creek NSW 2178  
Phone: 1300 788 780  
Email: [technicalservices@ardexaustralia.com](mailto:technicalservices@ardexaustralia.com)  
[www.ardexaustralia.com](http://www.ardexaustralia.com)

**ARDEX New Zealand Ltd**  
15 Alfred Street, Onehunga Auckland,  
New Zealand 1061  
Phone: 0800 227 339  
Email: [info@ardexnz.com](mailto:info@ardexnz.com)  
[www.ardex.co.nz](http://www.ardex.co.nz)

# ARDEX WPM 150

## 3mm Plain Bitumen Membrane

### PRODUCT DESCRIPTION

ARDEX WPM 150 is an A.P.P. (Atactic Polypropylene) Plastomeric type modified bitumen membrane, consisting of a specially formulated bituminous compound of distilled asphalt modified with selected high grade visco-elastic polymers and reinforced with a polyester reinforcement.

ARDEX WPM 150 is coated with either a sanded or talc top surface finish, while the bottom surface is embossed and protected by a heat sensitive polythene film. This type of finish for the lower surface has been chosen for two specific purposes:

- To act as a temperature gauge during application. When the film melts it shows that the compound is at the correct temperature.
- The embossing is to allow the gases to rapidly escape when heated to its correct installation temperature avoiding possible problems of bubbling and blistering.

### FEATURES

- Excellent cold flexibility to  $-5^{\circ}\text{C}$
- Combined reinforcement carrier
- High mechanical characteristics
- High puncture resistance
- Good elastic memory
- Good elongation

### USES

ARDEX WPM 150 is used within multi-layer waterproofing systems. ARDEX WPM 150 can be used for both horizontal or vertical applications, and for waterproofing balconies, terraces, rooftops, and tanking environments.

### SUBSTRATE PREPARATION

By way of mechanical methods and vacuum cleaning as necessary, remove all dirt, dust, curing compounds, oils, grease, surface sealers, and any other contaminants prior to application. Prepare surface to leave sound, clean, free from sharp edges, loose or other materials which may damage the membrane.

Damaged concrete between 2mm-30mm can be treated with ARDEX A46. Spalling concrete must be treated accordingly with the ARDEX Concrete Repair range such as ARDEX BR 345, please review the respective product data sheets on treating spalling concrete.

### SUBSTRATE PRIMING

Prior to the application of ARDEX WPM 150 all prepared concrete surfaces should be primed with ARDEX WPM 240 at a rate of  $5\text{m}^2\text{--}6\text{m}^2$  per litre and allowed to dry. Coverage rate will depend on the porosity of the substrate being treated.

### INSTALLATION

To ensure the correct shedding of water, the membrane must be installed from the lowest point of the area and work towards the highest point, in the direction of the slope. A layer of ARDEX WPM 150 should be completely unrolled and aligned. Using a suitable pressure roller and suitable LPG torch equipment, the membrane is to be applied using appropriate application techniques.

Using an LPG gas torch, fuse the laps of the ARDEX WPM 150 to form a continuous membrane layer, with minimum side laps of 100mm and minimum end laps of 120mm.

### TECHNICAL DATA

CHARACTERISTIC	TEST METHOD	NOMINAL VALUES
Length	EN 1848-1	10m
Width	EN 1848-1	1m
Thickness	EN 1849-1	3mm
Aeric Mass	EN 1849-1	3.5kg/m <sup>2</sup>
Shear Resistance Longitudinal Transverse	EN 12317-1	750 N/50mm 500 N/50mm
Tensile Strength Longitudinal Transversal	EN 12311-1	800 N/50mm 500 N/50mm
Elongation at Break Longitudinal Transversal	EN 12311-1	40% 50%
Resistance to Tearing (nail shank)	EN 12310-1	180 / 200N
Flexibility at Low Temperature	EN 1109	-5°C
Flow Resistance at Elevated Temperature	EN 1110	120°C
Surface Finishes	Lower <sup>1</sup> Top <sup>2</sup>	Torch Film Sand or Talc

Note 1) Lower surface; the surface which is applied to the structure being waterproofed.

Note 2) Top surface; exposed to underside of covering membrane.

### PACKAGING

Roll size: 1m x 10m

Roll weight: Approximately 35kg

Rolls per pallet: 28

### STORAGE

All rolls of ARDEX WPM 150 should be stored in a covered area protected against sunlight and UV radiation. Rolls should be stored in a vertical position on a smooth floor so as not to damage the edges.

# ARDEX WPM 150

## 3mm Plain Bitumen Membrane

---

### LIMITATIONS

ARDEX WPM 150 cannot be left UV exposed for extended periods. ARDEX WPM 150 is not designed as a foot trafficable membrane. New concrete must be cured at least 28 days.

Before any substrate preparation, installation or finishing methods relating to ARDEX product are undertaken, please be aware of any potential risks and use appropriate PPE (personal protective equipment). This may involve contacting substrate manufacturers for Safety Data Sheets.

### SAFETY DATA

Avoid contact with skin and eyes. In case of contact with the eyes rinse with running water until advised to stop by the Poisons Information Centre or a doctor, or for at least 15 minutes. Wear protective gloves, clothing, face and eye protection. Suspected of causing cancer. This product is combustible. On combustion, may emit toxic fumes of carbon monoxide (CO). Avoid inhaling dust/ fume/ gas/ mist/ vapours/ spray. If fumes or combustion products are inhaled remove from contaminated area. Ensure adequate ventilation during application. Check with your local Council regarding the disposal of contents. Call the Poisons Information Centre on 131 126 (AUS) and 0800 764 766 (NZ) or call a doctor if you feel unwell. At times updates can occur to data. To ensure you have the most current technical and safety information please consult the latest data sheets found on the product page at [www.ardexaustralia.com](http://www.ardexaustralia.com)

### GUARANTEE

ARDEX Australia Pty Ltd ("we" or "us") guarantees this product ("our goods") is free from manufacturing defects and will perform to any applicable specification published by us for 10 years from the date of purchase. Our liability under this guarantee is limited at our option to replacement of the product, repair of any damage to the immediate surface or area of application of the product, or compensation, in each case if we are satisfied loss or damage was due to a breach of this guarantee. This guarantee does not apply if damage or loss is due to failure to follow published instructions or any act or circumstance beyond our control, including shade variations and efflorescence. If you wish to make a claim under this guarantee you must notify us (ARDEX Australia Pty Ltd, 2 Buda Way Kempes Creek NSW 2178; Toll Free: 1800 224 070; Email: [technicalservices@ardexaustralia.com](mailto:technicalservices@ardexaustralia.com)) and provide evidence of your purchase of the product within 30 days of any alleged loss or damage occurring. We reserve the right to ask you for satisfactory evidence of any alleged loss or damage. Any claim under this guarantee is at your cost. This guarantee is in addition to any rights or remedies you may have as a "consumer" under the Australian Consumer Law and to that extent you need to be aware that: "Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and for compensation for any other reasonably foreseeable loss of damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure".

### DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable Australian Standards. Our instructions and recommendations are only for the uses they are intended. Users are advised to confirm that this product is suitable for their application and conforms with the specifications of the system. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may affect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

© ARDEX Australia Pty Ltd 2025.

All aforementioned products are the trade marks of ARDEX Australia Pty Ltd, its licensors and affiliates.

This data sheet was issued in January 2025 and is valid for 3 years, in some instances a newer version may be published. Always refer to [www.ardexaustralia.com](http://www.ardexaustralia.com) for the latest technical data from ARDEX Australia Pty Ltd.