

VOC Content Test Certificate

Wednesday, 19th July 2017

Supplier: Ardex Australia Pty Ltd (20 Powers Road, Seven Hills, NSW 2147).

Sample Description: Ardex WPM 185

Date Tested: July 2017 (Tested by FORAY Laboratories – NATA Accreditation 1231)

Test Method: Modified Method 304-91 Determination of Volatile Organic Compounds (VOC) in Various Materials as referenced by South Coast Air Quality Management District (SCAQMD) Rule 1168.

Test Data:

<p>Specification</p> <p>Green Building Council of Australia</p> <p>Green Star Design & As Built V1.1 13.1.1</p> <p>Green Star Interiors V1.1 12.1.1B</p>	<p>Ardex WPM 185</p>
<p>Acoustic sealants, architectural sealants, water proofing membranes and sealants, fire retardant sealants and adhesives:</p> <p>250 grams per Litre as VOC content per material</p>	<p>2 grams per Litre as VOC content per material</p>
<p><i>This test was modified to assess the VOC content of the solid membrane product Ardex WPM 185. As such, the result is calculated based on the VOC per Litre of solid product. This can be converted to a VOC result of 5.7g/m² of product based on a thickness of 3.3mm.</i></p>	



Dr. Vyt Garnys
PhD, BSc(Hons) AIMM, ARACI, ISIAQ
ACA, AIRAH, FMA
Managing Director and Principal Consultant



Tuan Duong
BE (Chem. Eng.)
Consultant



Nick Joy
BSc (Hons)
Consultant

CV170752