



TECHNICAL BULLETIN – TB297

CHEMICAL RESISTANCE OF ARDEX WPM822, WPM823 AND WPM813

3rd September 2024

INTRODUCTION & SCOPE

ARDEX supplies a range of urethanes that can be used in systems to create a waterproof and trafficable coating. This bulletin deals explicitly with the chemical resistance of three of these products: the ARDEX WPM 822, ARDEX WPM 823, and ARDEX WPM 813.

DEFINITIONS

ARDEX WPM822 is a two-part, UV-stable topcoat suitable for pedestrian traffic. It is used in conjunction with ARDEX WPM812 which is a waterproof membrane.

ARDEX WPM823 is a two-part, UV-stable topcoat suitable for vehicular traffic. It is used in conjunction with ARDEX WPM813 waterproof membrane.

ARDEX WPM 813 is a two-part, tough, and durable waterproof membrane.

On the next page is a guide to the chemical resistance of the above three products. Please note that it is a guide only and should not be used for specifications. Factors such as the time before it is in full service, the service temperature, and the degree of traffic may impact a recommendation. The chemicals in the table are in concentrated form unless otherwise stipulated. A service temperature of 23°C is assumed for this data. When considering a particular application, please contact ARDEX Technical Services.

The following terms are used in the table on the next page.

Fully Resistant	→	Recommended for continuous exposure
Resistant	→	General maintenance/housekeeping is required
Short-term resistant	→	Spill needs to be cleaned up in 2-4 hours
Not Resistant	→	It is not recommended to be exposed to this chemical



Building tomorrow

Liquid	Classification
Ammonia (10%)	Resistant
Ammonium Carbonate	Not Resistant
Ammonium Chloride	Fully Resistant
Brake Fluid ATE	Short-term Resistant
Calcium Chloride (40%)	Fully Resistant
Chlorine	Resistant
Cutting Oil	Short-term Resistant
Diesel Oil	Fully Resistant
Ethanol	Short-term Resistant
Ethyl Alcohol 100%	Short-term Resistant
Ethyl ether	Short-term Resistant
Glycerine	Resistant
Hydraulic Oil SAE90	Short-term Resistant
Hydrochloric Acid	Resistant
Jet Fuel	Resistant
Kerosene	Resistant
Magnesium Chloride (30%)	Fully Resistant
Methanol (<5%)	Short-term Resistant
Olive Oil	Resistant
Paraffin	Resistant
Petroleum	Fully Resistant
Petroleum ether	Resistant
Phosphoric acid (50%)	Not Resistant
Potash lye (10%)	Resistant
Potassium nitrate	Fully Resistant
Sea water	Resistant
Sodium chloride (10%)	Fully Resistant
Sulphuric acid (30%)	Short term resistant



Building tomorrow

IMPORTANT

This Technical Bulletin provides guideline information only and is not intended to be interpreted as a general specification for the application/installation of the products described. Since each project potentially differs in exposure/condition, specific recommendations may vary from the information contained herein. For recommendations for specific applications/installations, contact your nearest ARDEX Australia Office.

DISCLAIMER

The information presented in this Technical Bulletin is to the best of our knowledge true and accurate. No warranty is implied or given as to its completeness or accuracy in describing the performance or suitability of a product for a particular application. Users are asked to check that the literature in their possession is the latest issue.

REASON FOR REVISION-ISSUER

Change of slogan and address

DOCUMENT REVIEW REQUIRED

36 months or whenever third-party suppliers change their recommendations.

Australia: 1300 788 780

New Zealand: 643 384 3029

Web: www.ardexaustralia.com

email: technical.services@ardexaustralia.com

Address: 2 Buda Way, Kemps Creek NSW 2178