



## ANALYSIS CERTIFICATE


26 April, 2024

OUR REF:	111301A
TO:	Ardex NZ Ltd
ATTN:	Ines Jakob

SAMPLE OF:	Ardex P38	SAMPLE TYPE:	As received
SAMPLE TYPE:	One-component dispersion moisture barrier	DATE RECEIVED:	26/04/2024
SAMPLE DATE:	-	DATE TESTED:	26/04/2024
		ORDER NO:	-

	Result	Method
Total Non-Volatile Content, %w/w	24.6	Oven-drying @ 110°C (60mins)
Total Water Content, %w/w	71.7	Karl Fischer titration
Density, g/mL	1.10	Gravimetry
Exempt Compounds	None specified	

	Result	Method
Total Volatile Organic Compounds, g/L	41	SCAQMD METHOD 304-91

  
Analyst

  
Authorised by

This report relates only to the sample provided

**This Report Shall Not Be Reproduced Except In Full**  
**MEMBER OF THE NEW ZEALAND ASSOCIATION OF CONSULTING LABORATORIES**