



ARDEX WR 100

General Purpose Acrylic Render

Easy to use with superior non-slump and creamy consistency

Suitable for internal and external applications

Produces a build-up from 2-10mm with a fine finish, with no sagging or cracking

Suitable for a variety of substrates including masonry, AAC blocks and concrete

No maturing time required - can be applied immediately after mixing

ARDEX Australia Pty Ltd

20 Powers Road
Seven Hills NSW 2147
Phone: 1300 788 780
Email: technicalservices@ardexaustralia.com
Internet: www.ardexaustralia.com

ARDEX New Zealand Ltd

15 Alfred Street
Onehunga, Auckland, 1061
Phone: 0800 227 339
Email: info@ardexnz.com
Internet: www.ardex.co.nz

ARDEX WR 100

General Purpose Acrylic Render

DESCRIPTION

ARDEX WR 100 is a fine-grade acrylic render suitable for rendering walls, both internally and externally, at an application thickness from 2-10 mm. It can be applied over the following surfaces:

- Masonry (Brickwork & Blockwork)
- Concrete walls
- AAC - Autoclaved Aerated Concrete Blocks and Panels

SURFACE PREPARATION

The surface being adhered to must be clean, firm and free of dust, dirt, oil, grease, curing compounds, release agents and other barrier materials. Green concrete should be allowed to cure for 28 days prior to rendering. If dry and porous, dampen the surface to be rendered by brushing or sponging the surface or applying a light mist spray of water to prevent rapid drying of the render. Dense concrete will require priming with ARDEX WR PRIME and allowed to dry for 30 minutes prior to the application of the render. Use of a primer will extend the working time of the render.

MIXING

1. Add approximately 3.0 to 3.5L of clean water to a bucket.
2. Gradually add 20kg of ARDEX WR 100 to the water whilst mixing with an electric mixer to disperse the powder into a creamy, lump free consistency.

APPLICATION

1. Apply the render with a steel trowel, evenly spreading the mix over the surface.
2. A straight edge can be used to check for level or flatness of the render.
3. After 10-30 minutes, depending on ambient and surface conditions, work can begin on the surface finish. The surface finish can be dense and smooth by using a wooden or plastic float or coarse and sandy by using a sponge to give the required effect.
4. The mixed material is useable for up to 30- 40 minutes at 23°C and 50% relative humidity.

RECOMMENDED METHODS OF PREPARATION AND APPLICATION

Masonry (Brickwork & Blockwork)

Ensure that masonry and mortar is applied according to Australian Standard AS 3700 and is fully cured with joints applied. Clean off dust, oil, grease and all loose contaminating materials or coatings. If dry and porous,

dampen the surface to be rendered by brushing or sponging the surface or applying a light mist spray of water to prevent rapid drying of ARDEX WR 100.

A subsequent coat of ARDEX WR 100 may be applied after 4-8 hours depending on ambient conditions and application thickness. Before application of a decorative finish (i.e. paint or façade membranes such as ARDEX WPM 310 and WPM 330) allow the render to cure for a minimum of 1 day for each 2mm thickness of the render.

Concrete Walls

Clean off dust, oil, grease and all loose contaminating materials or coatings. If dry and porous, dampen the surface to be rendered by brushing or sponging the surface or applying a light mist spray of water to prevent rapid drying of ARDEX WR 100. If dense and non-porous, use ARDEX WR 100 with ARDEX WR Prime at a dilution rate of 1:5 (ARDEX WR Prime / water) for first coat. Concrete over 35MPa may require for the pores to be opened by mechanical means.

A subsequent coat of ARDEX WR 100 may be applied after 4-8 hours depending on ambient conditions and application thickness. Before application of a decorative finish (i.e. paint or façade membranes such as ARDEX WPM 310 and WPM 330) allow the render to cure for a minimum of 1 day for each 2mm thickness of the render.

AAC – Autoclaved Aerated Concrete Blocks and Panels

Clean off dust, oil, grease and all loose contaminating materials or coatings using a stiff brush. Prepare AAC blocks according to manufacturer's instructions. Apply 1-2 coats of ARDEX WR Prime; then use ARDEX WR 100 for first render coat. For AAC Panels, cover joints with alkali-resistant mesh tape to minimise cracking.

A subsequent coat of ARDEX WR 100 may be applied after 4-8 hours depending on ambient conditions and application thickness. Before application of a decorative finish (i.e. paint or façade membranes such as ARDEX WPM 310 and WPM 330) allow the render to cure for a minimum of 1 day for each 2mm thickness of the render.

FINISHING

After 10-30 minutes, depending on ambient and surface conditions, work can begin on the surface finish. The surface finish can be dense and smooth by using a wooden or plastic float or coarse and sandy by using a sponge to give the required effect.

ARDEX WR 100

General Purpose Acrylic Render

TILING OVER RENDER

The render must be applied at a minimum thickness of 2mm and have a sandy finish before tiling. Prime with ARDEX Multiprime and apply tiles with the recommended ARDEX adhesive for that type of tile. Please note, that weight loading limits apply for rendered surfaces; tiling must be performed in accordance with the current version of AS3958.

DRYING TIME

The render surface is touch dry in 1-2 hours @ 23°C. A subsequent coat may be applied after 4-8 hours depending on ambient conditions and application thickness and the surface will reach full cure after 7 days. Before application of a decorative finish (i.e. paint or façade membranes such as ARDEX WPM 310 and WPM 330) allow the render to cure for a minimum of 1 day for each 2mm thickness of the render. Cold, damp or humid conditions may lengthen the drying time.

COVERAGE

Coverage will vary depending on the condition of the surface and site conditions. As a guide, 20kg of ARDEX WR 100 mixes to 13 litres of mortar. As a guide, 20kg will cover:

- 6.5m² at 2mm thickness
- 2.6m² at 5mm thickness
- 1.3m² at 10mm thickness

PACKAGING

ARDEX WR 100 is packed in polylined paper sacks – net weight 20kg.

CLEAN UP

Clean all tools in water immediately after use.

SHELF LIFE

12 months when stored in the original unopened packaging, in a dry place at 23°C and 50% relative humidity.

Pay Attention to the following:

ARDEX WR 100 is not suitable for use over floors and is not suitable for application over painted surfaces, blueboard, EPS or PVC panels or existing renders. Adequate movement joints are required to minimise cracking on the surface of the render. To avoid damage and for ease of cleaning all windows and doors should be masked and covered. Do not apply in temperatures below 10°C or above 35°C or in extreme conditions such as high wind or direct sunlight and shelter from rain and moisture for 24 hours after completion.

Do not apply in swimming pools.

SAFETY DATA

This product may cause irritation and an allergic reaction to the skin. It may cause serious eye injury and irritation to the respiratory system. In case of contact with the eyes rinse with running water until advised to stop by the Poisons Information Centre or a doctor, or for at least 15 minutes. Wear protective gloves, clothing, eye and face protection. Avoid inhaling dust/fumes/gas/mist/vapours/spray. Ensure adequate ventilation during mixing and application. Store locked up. Check with your local Council regarding the disposal of contents, dispose of packaging thoughtfully and recycle where possible. Keep out of the reach of children. Call the Poisons Information Centre on 131 126 (AUS) and 0800 764 766 (NZ) or call a doctor if you feel unwell. Additional information is in the Safety Data Sheet (SDS) at www.ardexaustralia.com

ARDEX WR 100

General Purpose Acrylic Render

TECHNICAL DATA

Product Characteristics

Colour Light Grey Powder

Characteristics of Mix

Mixing Ratio 3 - 3.5L/20kg Powder

Application Properties

Pot Life 30-40 minutes

Touch Dry 1-2 hours

Recoat Time 4-8 hours

Full Cure 7 days

GUARANTEE

ARDEX Australia Pty Ltd ("we" or "us") guarantees this product ("our goods") is free from manufacturing defects and will perform to any applicable specification published by us for 10 years from the date of purchase. Our liability under this guarantee is limited at our option to replacement of the product, repair of any damage to the immediate surface or area of application of the product, or compensation, in each case if we are satisfied loss or damage was due to a breach of this guarantee. This guarantee does not apply if damage or loss is due to failure to follow published instructions or any act or circumstance beyond our control, including shade variations and efflorescence. If you wish to make a claim under this guarantee you must notify us (ARDEX Australia Pty Ltd, 20 Powers Road Seven Hills NSW 2147; Toll Free: 1800 224 070; Email: technicalservices@ardexaustralia.com) and provide evidence of your purchase of the product within 30 days of any alleged loss or damage occurring. We reserve the right to ask you for satisfactory evidence of any alleged loss or damage. Any claim under this guarantee is at your cost. This guarantee is in addition to any rights or remedies you may have as a "consumer" under the Australian Consumer Law and to that extent you need to be aware that: "Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and for compensation for any other reasonably foreseeable loss of damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure".

DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable Australian Standards. Our instructions and recommendations are only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice building regulations or industry guidelines may affect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

© ARDEX Australia Pty Ltd 2019.

All aforementioned products are the trade marks of ARDEX Australia Pty Ltd, its licensors and affiliates.

This datasheet was issued in October 2019 and is valid for 3 years, in some instances a newer version may be published. Always refer to www.ardexaustralia.com for the latest technical data from ARDEX Australia Pty Ltd.