

Friday August 7th, 2009

Manufacturer: Ardex Australia Pty Ltd (Unit 7, 20 Powers Road Seven Hills NSW 2147)

Sample Description: Ardex WA grouting compound

Date Tested: July 2009 (Tested by FORAY Laboratory - NATA Accreditation 1231)

Test Method: SCAQMD Method 304-91 Determination of Volatile Organic Compounds (VOC) in Various Materials as referenced by South Coast Air Quality Management Division (SCAQMD) Rule 1168.

Test Data:

Specification Green Building Council of Australia Green Star Office Design V2 IEQ-13 Green Star Office Interiors V1.1 IEQ-11	Ardex WA
Ceramic tile adhesive 65 grams per Litre as VOC content material	20 grams per Litre as VOC content material
Specification Green Building Council of Australia Green Star Office Design V3 IEQ-13	Ardex WA
Ceramic tile adhesive 65 grams per Litre as VOC content material	20 grams per Litre as VOC content material

Dr. Vyt Garnys PhD, BSc(Hons) AIMM, ARACI, ISIAQ ACA, AIRAH, FMA Managing Director and Principal Consultant

F0907-28