



TECHNICAL BULLETIN – TB026

ARDEX UNDERLAYMENTS FOR STATIC CONTROL VINYL

3rd October 2024

INTRODUCTION & SCOPE

Computer, electronics, and telecommunications installations, hospital operating theatres, preparation rooms, defence establishments, telephone exchanges, ordinance manufacture, and storage facilities often require the use of “Static Control” Vinyl Floor Coverings to minimise or eliminate the risk of electrostatic discharge.

Static-control vinyl Flooring requires a substrate of known resistance. Concrete subfloors' electrical conductivity can vary greatly, and their resistance may be lower than the minimum stated in the “Static Control” Vinyl Flooring specifications.

A recent system introduced into health care facilities is electrosensitive matting placed under the flooring to detect falls by patients.

ARDEX K15 and ARDEX K12 (both incorporating ARDEX E25) and ARDEX K55 Self Smoothing Cement underlayments installed at a minimum thickness of 3 mm provide the necessary isolation barrier of known resistance beneath the “Static Control Vinyl Flooring” and also a rapid-drying underlayment for the matting's special requirements.

The following procedure is for use where “Static Control” Sheet Vinyl requires a minimum 3mm isolating layer of self-smoothing cement underlayment and a copper strap earthing system is applied to the underlayment.

The matting system requires a flat, smooth and dry subfloor system.

INSTALLATION PROCEDURES

PRIMING

Concrete floors must be structurally sound with all previous coatings removed, clean and free of oil, grease, wax, latex compounds, curing compounds, efflorescence, laitance, dust and all foreign matter, back to an open porous matrix of the concrete.

Professional cleaning by mechanical means in line with sound building industry practices is advised and suggested cleaning & preparation methods in line with those recommended in ARDEX Technical Bulletin TB041 and AS1884-2012. Methods recommended include shot blasting, scarifying, or diamond grinding to provide a surface profile between CSP3 to CSP7.

APPLICATION

The primer for standard absorbent concrete is ARDEX P51. Mix ARDEX P51 1:2 with water and apply evenly with a soft push broom. Do not leave any bare spots, and remove all puddles and excess primer. Allow to dry to a clear, thin film (minimum 3 hours max. 24 hours). The underlayment should not be applied until the primer is dry.

The recommended cement-based self-smoothing underlayment is ARDEX K55 or either ARDEX K15 or ARDEX K12 Self-Smoothing Cement. The additive to be mixed with ARDEX K15M or ARDEX K12N is ARDEX E25 Resilient Emulsion as follows -



K15M	20kg powder	1.6 litres E25	4.0 litres water
K12N	20kg powder	1.0 litres E25	4.5 litres water

The underlayment is to be applied at a minimum of 3mm over the highest point in the floor.

Notes:

Where "Static Control" type flooring is installed, it is usual to check that the completed floor's conductivity is not higher than the maximum required as specified by the "Static Control" Vinyl Flooring manufacturer. Always refer to the Flooring Manufacturer for specific "Static Control" requirements.

The electrosensitive matting requires critical moisture levels so that moisture barrier systems may be necessary under the smoothing cement, and the underlayment needs to be fully cured and dried.

Where the subfloor is metal decking, ARDEX Technical Services can provide advice or refer to ARDEX Technical Bulletins TB100.

Particle board and similar wooden floors are not suitable for this system.

IMPORTANT

This Technical Bulletin provides guideline information only and is not intended to be interpreted as a general specification for the application/installation of the products described. Since each project potentially differs in exposure/condition, specific recommendations may vary from the information contained herein. For recommendations for specific applications/installations, contact your nearest Ardex Australia Office.

DISCLAIMER

The information presented in this Technical Bulletin is to the best of our knowledge true and accurate. No warranty is implied or given as to its completeness or accuracy in describing the performance or suitability of a product for a particular application. Users are asked to check that the literature in their possession is the latest issue.

REASON FOR REVISION-ISSUER

Change of slogan and address

DOCUMENT REVIEW REQUIRED

36 months or whenever third-party suppliers change their recommendations.

Australia: 1300 788 780

New Zealand: 643 384 3029

Web: www.ardexaustralia.com

email: technical.services@ardexaustralia.com

Address: 2 Buda Way, Kemps Creek NSW 2178